

Project:

Order No: Premio EPS80 Carbon Compression test

Tester: Thümler GmbH-Z5


Part No: P80Carbon/2018_08_27(4)

Method: MSZ EN 826

Customer: Premio Hungária

Execution date: 2018. 08. 27. 12:51:55

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80Carbon/2018_08_27(4)	81,27	9,99
P80Carbon/2018_08_27(4)	82,84	10,00
P80Carbon/2018_08_27(5)	79,33	9,99
P80Carbon/2018_08_27(7)	80,19	10,00
Max.	82,84	10,00
Min.	79,33	9,99
Mean	80,91	9,99